

Features	Test Method	Fixed Value		
<b>Dimensions And Appearance</b>	ISO 10545-2	Compliant		
<b>Water Absorption</b>	ISO 10545-3	≤ 0.1%		
<b>Flexural Resistance</b>	ISO 10545-4	> 45 N/mm <sup>2</sup>		
<b>Modulus Of Rupture ( Thickness )</b>	ISO 10545-4	8.5mm	2500N	
		12mm	5000N	
		14mm	6500N	
		20mm	11000N	
<b>Resistance to Deep Abrasion</b>	ISO 10545-6	<140 mm <sup>3</sup>		
<b>Resistance to Surface Abrasion</b>	ISO 10545-7	As Indicated In The Catalog		
<b>Linear Expansion Thermic Coefficient</b>	ISO 10545-8	≤ 7X10 <sup>-6</sup> C <sup>-1</sup>		
<b>Resistance to Sudden Temperature Changes</b>	ISO 10545-9	Resistant		
<b>Frost Resistance</b>	ISO 10545-12	Resistant		
<b>Resistance of Chemical Attack</b>	ISO 10545-13	High Concentration	Low Concentration	Domestic Chemicals
		Available On Request	GLA, GLB to GLC ULA, ULB to ULC	min. UB / GB
<b>Stain Resistance</b>	ISO 10545-14	Min. 3		
<b>Dynamic Coefficient of Friction (DCOF)</b>	ANSI A137.1	> 0.42 Wet		
<b>Colour Stability to Light</b>	DIN 51094	Compliant		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Through Body Porcelain Tile
- Matte | Honed | Bush-Hammered Finishes
- 10.5mm Thickness
- Rectified Edge
- V2 - Slight Shading Variation
- Frost Resistance = Yes

