

Features	Test Method	Value
Length and Width	ISO 10545-2	$\pm 0.6\% \pm 2 \text{ mm}$
Thickness		$\pm 5\% \pm 0.5 \text{ mm}$
Warpage of Edges		$\pm 0.5\% \pm 1.5 \text{ mm}$
Wedging		$\pm 0.5\% \pm 2 \text{ mm}$
Flatness		$\pm 0.5\% \pm 2 \text{ mm}$
Water Absorption	ISO 10545-3	$\leq 0.5\%$
Bending Strength	ISO 10545-4	$R \geq 35 \text{ N/mm}^2$
Coefficient of Linear Thermal Expansion	ISO 10545-8	$7 \times 10^{-6} \text{ C}^{-1}$
Thermal Shock Resistance	ISO 10545-9	Resistant
Frost Resistance	ISO 10545-12	Resistant
Chemical Resistance	ISO 10545-13	Resistant
Stain Resistance	ISO 10545-14	$\geq \text{Class 3}$
Color Resistance to Light	DIN 51094	No Alteration
Slip Resistance	DIN 51130	$9 \leq R \leq 13$
	DIN 51097	A, B, C

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- 8.5mm Thickness
- Pressed Edge
- V2 - Slight Shading Variation
- Frost Resistance = No


www.genrose.com