

Features	Test Method	Value
Length and Width	ISO 10545-2	± 0.3mm ± 0.3% / ± 0.5%
Thickness		± 0.2mm ± 2.1%
Straightness of Sides		± 0.5mm ± 0.6% / ± 0.11%
Rectangularity		± 0.5mm ± 0.6% / ± 0.11%
Surface Flatness		+ 1.2mm / - 0.5mm + 0.18% / - 0.08%
Center Curvature		
Edge Curvature		
Warpage		
Water Absorption		ISO 10545-3
Breaking Strength	ISO 10545-4	≥ 1300 N
Modulus of Rupture		≥ 35 N/mm ²
Abrasion Resistance	ISO 10545-7	4
Frost Resistance	ISO 10545-12	Required
Fire Resistance	EN -14411	A1
Resistance to Low Concentrations of Acids and Alkalis	ISO 10545-13	Min. Type GLB
Resistance to High Concentration of Acids and Alkalis		Min. Type GHB
Resistance to Domestic Cleaning Products		Min. Type GA
Resistance to Household Chemicals and Swimming Pool Salts		Min. Type GA
Stain Resistance	ISO 10545-14	Min. Type 3
Recycled Content	-	Min. 38%

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Semi Polished Finish
- 9.6mm Thickness
- Rectified Edge
- PEI Rating = 4
- V3 - Moderate Variation
- Frost Resistance = Yes

