

Features	Test Method	Value			
		N < 7cm	7cm ≤ N < 15cm	N ≥ 15cm	
Length and Width	ISO 10545-2	± 0.5mm	± 0.9mm	± 0.6mm	± 2mm
Thickness		± 0.5mm	± 0.5mm	± 0.5mm	± 0.5mm
Straightness of Sides		N/A	± 0.75mm	± 0.5mm	± 1.5mm
Squareness		N/A	± 0.75mm	± 0.5mm	± 2mm
Planarity		N/A	± 0.75mm	± 0.5mm	± 2mm
Water Absorption	ISO 10545-3	< 0.5%			
Bending Strength	ISO 10545-4	≥ 35 N / mm <sup>2</sup>			
Deep Abrasion Resistance	ISO 10545-6	≤ 175 mm <sup>3</sup>			
Abrasion Resistance	ISO 10545-7	5 = Light Grey   White 4 = Blu   Denim   Green   Ocra   Sea Water 3 = Cotto			
Frost Resistance	ISO 10545-12	Resistant			
Resistance to Low/High Concentrations of Alkalis and Acids	ISO 10545-13	Minimum Class B			
Resistance to Household Chemical Products and Swimming Pool Additives					
Stain Resistance	ISO 10545-14	Class 3			
Hardness in Mohs Degrees	UNI EN 101	≥ 5° Mohs			
Dynamic Coefficient of Friction (DCOF)	ANSI A137.1:2012	> 0.42			
Recycled Content	-	52%			



This product will contribute to GBC Italia registered LEED projects.  
Low Emissions Material • Zero VOC

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Glazed Porcelain Tile
- Polished Finish
- 9.5mm Thickness
- Pressed Edge
- PEI Rating = 5 (Light Grey | White)  
4 (Blu | Denim | Green | Ocra | Sea Water )  
3 (Cotto)
- V3 - Moderate Shading Variation
- Frost Resistance = Yes

**Disclaimer:** DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.



[www.genrose.com](http://www.genrose.com)