

Features	Test Method	Value
Water Absorption	ASTM C373	≤ 0.1%
Bond Strength	ASTM C482	≥ 200 psi
Warpage average	ASTM C485	≤ 0.40%
Thickness Dimension	ASTM C499	≤ 0.04 in
Facial Dimension		≤ 0.25%
Wedging Average	ASTM C502	≤ 0.25%
Breaking Strength	ASTM C648	≥ 350 lbf
Chemical Resistance	ASTM C650	Class A
Frost Resistance	ASTM C1026	No evidence of damage
Visible Abrasion Resistance for Glaze Tile	ASTM C1027	Class 4
Stain Resistance	ASTM C1378	Class A
Coefficient of Friction (Dynamic)	DCOF Acutest (WET) <sup>sm</sup>	≥ 0.42
Aesthetic Classification	Visual Evaluation Shade & Texture	V2
Deep Abrasion	ASTM C1243	< 150 mm <sup>2</sup>
Hardness	MOHS	≥ 7
Recycled Content	-	≥ 40%

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Glazed Porcelain Tile
- Honed Finish
- Rectified Edge
- PEI Rating = 5
- V2 - Slight Shading Variation
- Frost Resistance = Yes


[www.genrose.com](http://www.genrose.com)