

Features	Test Method	Value
Water Absorption	ASTM C373	14.8%-17.1% <sup>2</sup>
Breaking Strength	ASTM C648	≥ 150 lbf. avg
Linear Thermal Expansion	ASTM C372	Conforms
Thermal Shock Resistance	ASTM C484	Conforms
Chemical Resistance	ASTM C650	Conforms
Stain Resistance	ASTM C1378	Conforms
Frost Resistance	ASTM C1026	No
Bond Strength	ASTM C482	Conforms
Thickness	ASTM C499	max ± 0.030 inch
Surface Hardness	Mohs Scale	5 Mohs
Warpage Edge	ASTM C485	Conforms
Warpage Diagonal	ASTM C485	Conforms
Recycled Content	-	7%



This product will contribute to USGBC registered LEED projects.  
It will also contribute to the ANSI approved NAHB Green Building Standard ICC 700.  
Low Emissions Material • Zero VOC

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Ceramic Wall Tile
- Matte | Glossy Finishes
- 7mm | 7.8mm Thicknesses
- Pressed Edge
- V1 - Uniform Appearance
- Frost Resistance = No



[www.genrose.com](http://www.genrose.com)